

ATECH is a series of sheets based on ABS which is a raw material with very high impact-strength. ABS also has impressive thermal qualities and is easy to thermoform and fabricate. The ATECH 3200 is a super high impact ABS with a top layer of high gloss PMMA (acrylic).

ALSO AVAILABLE IN:

- ATECH 3203 with extra UV stabilization added in ABS to improve weather resistance (3-5y)
- ATECH 3206 with extra UV stabilization added in ABS and PMMA (10y)
- Optional with different structures to combine the high gloss surface
- Dual colouring to optimize to your need

RECYCLING

Our total recycling concept (TRC), is a major advantage in today's environmentally friendly market. The TRC concept covers all types of sheets to provide you with cost saving. Off-cuts from the sheets can be used in production of new sheets by co-extruding virgin material as the top layer. Care is taken that all quality requirements are met.

ATECH® 3200 BENEFITS:

- Super high gloss surface finish
- Different stages of weathering performance solutions
- Easy to thermoform
- High impact strength
- Good thermal qualities

APPLICATION AREAS:

Suitable for demanding external automotive component parts which are exposed to UV light, and other tough industrial applications where a high gloss finish is required.

DELIVERY PROGRAM:

Standard size: 1250 x 2050 mm

Max width: 1750 mm

Thickness range: 2 – 8 mm

Colours: Standard colours and customer specific colours upon request

Embossing: 00/00, 00/35, 00/38, 00/40, 00/50, 00/60

ATECH® 3200 TECHNICAL SPECIFICATIONS

Property	Value	Unit	Standard
Physical properties			
Density	1,07	g/cm ³	ISO 1183
Mechanical properties			
Tensile strength at yield	33	MPa	ISO 527
Tensile elongation at yield	>2	%	ISO 527
Tensile elongation at break	45	%	ISO 527
Elastic modulus in tension	2000	MPa	ISO 527
Flexural strength	55	MPa	ISO 178
Flexural modulus	2000	MPa	ISO 178
Izod impact, notched +23 °C	23	kJ/m ²	ISO 180
Izod impact, unnotched -18 °C	20	kJ/m ²	ISO 180
Izod impact, unnotched -35 °C	10	kJ/m ²	ISO 180
Ball indentation hardness	77	MPa	ISO 2039
Thermal properties			
Linear coefficient of thermal expansion (20-70 °C)		K ⁻¹	ISO 11359-2
Vicat softening temperature B120	97	°C	ISO 306
Heat deflection temperature HDT-A	86	°C	ISO 75
Mould shrinkage	0,6 - 0,7	%	ISO 294-4

Properties reported here are typical values. Arla Plast makes no representation that the material in any particular shipment will conform exactly to the values given. The above information is based upon experience and given in good faith. Due to many factors which are outside our knowledge and control, no warranty is given or is to be implied with respect to such information. Detailed product specification and technical manual/information is available on request.