

MAKROVISION™ is extruded high optical quality transparent polycarbonate sheet. The product is extruded with advanced technology using the vast knowledge of our production team experienced in producing mono, co and tri-extrusion.

MAKROVISION™ is produced to achieve low dioptre and highest optical quality. The technical measurement of dioptre is according to DIN 52305.

The product is virtually unbreakable with extremely high impact resistance and offers high temperature performance too. The product provides designers, specifiers and architects with possibilities to use the sheets in applications where high optical quality is required replacing glass and other transparent plastics. The consistent high quality demands from the market helps to improve optical quality, machining, screen printability and thermoformability

ALSO AVAILABLE:

MAKROVISION™ is also available with Hard coat, SAPHIR® MAKROVISION.

EXCELLENT FIRE PERFORMANCE complying requirements to EN 13501-1 (EUROPEAN BUILDING STD). In case of fire, the sheet will melt and allow venting where heat and smoke will be let out and therefore reduce the growth of fire by flame spread.

MAKROVISION™ BENEFITS:

- Outstanding optical quality
- Dioptre measurement - DIN 52305
- More than 10 times the impact strength of high impact PMMA
- Half the weight of glass

APPLICATION AREAS:

For applications where high optical quality is required such as: lamination applications, windows, machine protection, safety glazing, ice hockey rinks, vandal protection, sound walls, ballistics protection etc.

DELIVERY PROGRAM:

Standard size: 2110 x 3050 mm

Thickness range: 3 - 10 mm

Colour: Clear

Embossing: No

Special sizes and thicknesses on request

MAKROVISION™ TECHNICAL SPECIFICATIONS

Property	Value	Unit	Standard
Physical properties			
Density	1,2	g/cm ³	ISO 1183
Refractive index (20 °C)	1,586		ISO 489
Moisture absorption 24 hours, 23 °C, 50% RH	0,15	%	ISO 62
Mechanical properties			
Tensile strength at yield (at break)	60 (70)	N/mm ²	ISO 527
Elongation at yield (at break)	6 (110)	%	ISO 527
Elastic modulus	>2300	N/mm ²	ISO 527
Flexural modulus	>2300	N/mm ²	ISO 178
Charpy unnotched impact strength -40 °C	NB	kJ/m ²	ISO 179/1eU
Charpy notched impact strength -30 °C	11	kJ/m ²	ISO 179/1eA
Izod notched impact strength +23 °C	65	kJ/m ²	ISO 180/1A
Izod notched impact strength -30 °C	10	kJ/m ²	ISO 180/1A
Thermal properties			
Linear coefficient of thermal expansion (20-70 °C)	65x10 ⁻⁶	K ⁻¹	ISO 11359-2
Heat deflection temperature, HDT A (1,80 N/mm ²)	132	°C	ISO 75
Heat deflection temperature, HDT B (0,45 N/mm ²)	142	°C	ISO 75
Vicat temperature VST/B 120	149	°C	ISO 306
Vicat temperature VST/B 50	148	°C	ISO 306
Thermal conductivity	0,20	W/m.K	DIN 8302
Electrical properties			
Volume resistivity, dry	>10 ¹⁴	Ω . m	IEC 60093
Surface resistivity, dry	10 ¹⁶	Ω	IEC 60093
Dielectric strength, dry	30	kV/mm	IEC 60243
Dielectric constant, dry 50 Hz	3		IEC 60250
Dielectric constant, dry 1 MHz	2,9		IEC 60250
Dissipation factor (tan δ), dry 50 Hz	0,001		IEC 60250
Dissipation factor (tan δ), dry 1 MHz	0,01		IEC 60250

Properties reported here are typical values. Arla Plast makes no representation that the material in any particular shipment will conform exactly to the values given. The above information is based upon experience and given in good faith. Due to many factors which are outside our knowledge and control, no warranty is given or is to be implied with respect to such information. Detailed product specification and technical manual/information is available on request.